



# HEVEA MATS

HeveaMats ApS  
Adresse: Tirslundvej 34, 6650 Brørup  
Tlf: +45 61669044  
Email: [info@HeveaMats.dk](mailto:info@HeveaMats.dk)  
Web: [www.HeveaMats.dk](http://www.HeveaMats.dk)

## Datablad Clever 33

### Dansk

Anvendelse	Legepladsen, haven, terrassen, altanen, fodboldbanen osv.
------------	---

Fiber	Polyethylen og polypropylen
-------	-----------------------------

Antal fiber	6.250 Dtex
Produktionsmetode	Tufted - 3/8"
Primær baggrund	100% Polypropylen m. fiberlås fleece
Sekundær baggrund	SBR-gummi; ca. 650 gr/m <sup>2</sup>
Strå	16.275 /m <sup>2</sup> (+/- 10%)
Højde strå	33 mm. (+/- 10%)
Total højde strå	35 mm. (+/- 10%)
Strå vægt	8.30 g/m <sup>2</sup> (+/- 10%)
Total vægt	1.640 g/m <sup>2</sup> (+/- 10%)

Fyld	Sand (> 80% rund), 5-10 kg/m <sup>2</sup>
------	---

Rulle bredde	200 cm eller 400 cm
Rulle længde	I henhold til lay-out

Farve	Grøn
-------	------

UV-stabilitet	> 6000 timer
Vandpermeabilitet	60 liter/min/ m <sup>2</sup>

## Engelsk

Employment	The playground, the garden, the terrace, the balcony, the football pitch, etc.
------------	--

Fibre	Polyethylene and Polypropylene
-------	--------------------------------

Yarn Detex	6.250 Dtex / 14 ply
Production method	Tufted - 3/8"
Primary backing	100 % PP with fibre-lock fleece
Secondary backing	SBR Latex; aprox 650 gr/m <sup>2</sup>
Stitches	16.275 /m <sup>2</sup> (+/- 10%)
Pile height	33 mm. (+/- 10%)
Total height	35 mm. (+/- 10%)
Pile weight	8.30 gr / m <sup>2</sup> (+/- 10%)
Total weight	1.640 gr / m <sup>2</sup> (+/- 10%)

Infill	Sand (> 80% round), 5-10 kg/m <sup>2</sup>
--------	--

Roll Width	200 or 400 cm
Roll Length	As per lay-out

Colour	Green
--------	-------

UV-Stability	> 6.000 hours
Water Permeability	60 liter/min/ m <sup>2</sup>