



HEVEA MATS

HeveaMats ApS
Adresse: Tirslundvej 34, 6650 Brørup
Tlf: +45 61669044
Email: info@HeveaMats.dk
Web: www.HeveaMats.dk

Datablad Speed 12

Dansk

Anvendelse	Legepladsen, multisport, alt form for sport, fitness osv.
------------	---

Fiber	Polyethylen og polypropylen
-------	-----------------------------

Antal fiber	9.000 Dtex
Produktionsmetode	Tufted - 3/8"
Primær baggrund	100% Polypropylen
Sekundær baggrund	SBR-gummi
Strå	31.500 /m ² (+/- 10%)
Højde strå	12 mm. (+/- 10%)
Total højde strå	14 mm. (+/- 10%)
Strå vægt	1.104 g/m ² (+/- 10%)
Total vægt	2.214 g/m ² (+/- 10%)

Fyld	Sand (> 80% rund), 5-10 kg/m ²
------	---

Rulle bredde	200 cm eller 400 cm
Rulle længde	I henhold til lay-out

Farve	Grøn, æblegrøn, sort, hvid, rød, blå, gul, grus, teak sort og uni teak
-------	--

UV-stabilitet	> 6000 timer
Vandpermeabilitet	60 liter/min/ m ²

Engelsk

Employment	The playground, multisport, all kind of sport, fitness etc.
------------	---

Fibre	Polyethylene and Polypropylene
-------	--------------------------------

Yarn Detex	9.000 Dtex / 14 ply
Production method	Tufted - 3/8"
Primary backing	100 % PP
Secondary backing	SBR Latex
Stitches	31.500 /m ² (+/- 10%)
Pile height	12 mm. (+/- 10%)
Total height	14 mm. (+/- 10%)
Pile weight	1.104 gr / m ² (+/- 10%)
Total weight	2.214 gr / m ² (+/- 10%)

Infill	Sand (> 80% round), 5-10 kg/m ²
--------	--

Roll Width	200 or 400 cm
Roll Length	As per lay-out

Colour	Green, Emerald Apple green / Black / White / Red / Blue / Yellow / Antracite / Gravel / Teak + Black and Uni Teak
--------	---

UV-Stability	> 6.000 hours
Water Permeability	60 liter/min/ m ²